



Tamper-Indicating Label Material

7381 • 7384

Technical Data

November, 2005

Product Description 3M™ Tamper-Indicating Label Materials are designed to provide a “void” message in the facestock when removal is attempted.

Construction	Product Number	Facestock	Destruct Pattern	Adhesive	Liner
	3M™ Tamper-Indicating Label Material 7381	2.0 mil (50 microns) Gloss White Polyester	“VOID”	1.0 mil (25 microns) #300 “Hi-Strength” Acrylic	3.2 mil (80 microns) 55# Densified Kraft
	3M™ Tamper-Indicating Label Material 7384	2.0 mil (50 microns) Gloss Bright Silver Polyester	“VOID”	1.0 mil (25 microns) #300 “Hi-Strength” Acrylic	3.2 mil (80 microns) 55# Densified Kraft

Features

- The compact format of the “void” message permits manufacture of small labels (1/2" x 1-1/4").
- 3M™ Adhesive 300 provides high bond to most surfaces.
- Durable polyester facestock withstands harsh environments.
- 55# densified kraft liner assures consistent die cutting.
- 3M label material 7381 is UL recognized in files MH 11410 and MH 16411 and CSA accepted file 99316. See the UL and CSA listing for details.
- 3M label material 7384 is UL recognized in file MH 11418.

Application Ideas

- Non-transferable labels for automotive, appliance and electronics industries.
- Tamper-indicating labels and seals for over-the-counter drugs and other packaging applications.

3M™ Tamper-Indicating Label Material

7381 • 7384

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Assume all surfaces to which these label materials will be applied are contaminated – metals may be oily or dusty; plastics may be coated with mold release agents, dirt, etc. Any surface contaminant will adversely affect adhesion and the destruct message; therefore, it must be removed prior to application by wiping with a solvent. Consult the manufacturer’s Material Safety Data Sheet for proper handling and storage of solvents.

Adheres to the following clean surfaces:

Stainless Steel	Painted Metal	Nylon
ABS	Polyester	Glass
Polypropylene	HDPE	Polycarbonate

Proper Handling and Storage:

Clean Substrate: Wet the application surface with a mild solvent such as isopropyl alcohol (rubbing alcohol) or heptane and wipe thoroughly.
Dry the surface with a lint free cloth before the solvent evaporates from the surface.

Application Pressure: Sufficient application pressure and dwell time is required to develop adhesion to assure “void” message appears both on facestock and substrate upon removal or upon attempted removal through tampering. Higher initial bonds can be achieved through increased application pressure such as firm hand or squeegee pressure.

Dwell Time: 24 hours at room temperature or 72°F (22°C) before testing.

Liner Release: 180° peel angle

Rate of Removal	Gram/Inch	N/100 mm
90 inches/minute	25 max.	0.96

Conformability:

Semi-rigid, suitable for flat or slightly curved surfaces.

Environmental Performance

Note: The following tests are intended as a guide to product performance. Application testing is recommended using actual substrates, expected dwell times, and actual conditioning for best determination of product suitability.

The properties defined are based on the adhesion of the label material to a stainless steel test surface.

Chemical Resistance: Bond is secure when exposed to the following:

Gasoline -	1 hr. at room temperature
Auto Oil -	72 hrs. at 120°F (49°C)
Weak Alkali -	4 hrs. at room temperature
Weak Acid -	4 hrs. at room temperature
MEK -	1 hr. at room temperature
Freon® TF -	1 hr. at room temperature
NaCl Solution -	72 hrs. at room temperature

Water Resistance: Withstands exposure to water at room temperature for 72 hours.

Temperature Resistance: Withstands exposure from -40°F (-40°C) to 250°F (121°C).

Humidity Resistance: Withstands exposure to 90°F (32°C) and 90% RH for 168 hours.

3M™ Tamper-Indicating Label Material

7381 • 7384

Processing

Incoming Label Materials:

Every slit roll has been tested for the presence of “void” message. The leading edge of every slit roll is tabbed with a 1-1/2" strip to simulate tampering, thereby indicating that the “void” message is functional on the leading edge of that roll.

Printing:

Caution should be exercised to avoid covering the surface of the label with opaque graphics to the extent that the “void” message is hidden, and the effectiveness of the label or seal is lessened.

Die-Cutting:

The compact “void” message permits manufacture of labels as small as 1/2" x 1-1/4" (13 mm x 32 mm).

It is recommended that the converter test for the presence of the “void” message on every roll of labels or seals as the converter processes them, to insure the product quality and consistency. This can be done by laminating a label or seal to an untreated polyester film test surface. The label or seal should be wiped down with a squeegee, allowed to dwell 10 minutes and then removed to observe the presence and functions of the “void” message on both the facestock and the substrate. It is also recommended that the converter test each lot of labels or seals on the actual application surface to assure the function of the “void” message.

Dispensing:

Care should be taken not to disturb the tamper-indicating feature by pre-destructing the “void” message when manually removing the label from the liner. Slowly remove the liner from the label at a 90° angle. It is recommended that the end user test samples for each roll of labels or seals received from the converter. This should be done by laminating a representative label or seal to the specific application surface to assure its function meets expectations. This test can be run after 10 minutes dwell. However, final judgement should be based on 72 hours dwell at room temperature prior to testing.

Application:

The tamper-indicating mechanism (i.e. the “void” message both on the facestock and on the substrate) depends upon adequate adhesion of the label to the substrate. A sufficient bond may not develop on all surfaces due to low surface energy (e.g. Teflon®), contaminated or textured surfaces. Therefore, it is important to determine the suitability of the product in the intended application by carefully pretesting. The primary function of the products is to effect a non-transferable (non-reusable) label or seal by causing the “void” message to appear on the facestock when removal from the substrate is attempted. As a result of the primary function, a “void” message is also transferred to the substrate. This message transferred to substrate can be removed by hand rubbing or by solvent wiping.

Our tamper-indicating product line is designed to indicate tampering by destructing when an attempt is made to remove the label. Since no tamper-indicating feature is 100% tamper proof, careful consideration must be taken when designing labels and seals. When the consequences of tampering could be severe, such as injury or loss of human life or significant monetary loss, these products aren't recommended as the sole means of package or product tamper indication. In these instances, additional methods in combination with the labels should be considered so that the tamper-indicating features are commensurate with the requirements of the application.

3M™ Tamper-Indicating Label Material

7381 • 7384

Storage Store at room temperature conditions of 72°F (22°C) and 50% relative humidity.

Shelf Life If stored under proper conditions, product retains its performance and properties for two years from date of manufacture.

Product Use All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

Warranty and Limited Remedy Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.

Limitation of Liability Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001:2000

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.

3M

**Industrial Business
Converter Markets
Industrial Adhesives and Tapes Division**

1030 Lake Road
Medina, OH 44256-0428
800-422-8116 • 877-722-5072 (fax)
www.3M.com/converter



*Recycled Paper
40% pre-consumer
10% post-consumer*

Freon and Teflon are registered trademarks of E.I. DuPont de Nemours & Co. Inc. Printed in U.S.A.
©3M 2005 70-0709-4599-6 (11/05)