



# Polyester Overlaminating Film 7742

## Product Data Sheet

Updated : July 2000  
Supersedes : March 1995

**Description :**

Premium overlaminate performance for extreme environmental conditions.

Superior abrasion, humidity and solvent resistance.

U.V. exposure resistant for extended periods of time.

Premium clarity films will not impart haze on underlying graphics.

#400 "Hi-Tack" Acrylic Adhesive offers premium adhesive performance to a wide variety of surfaces.

Specifically designed for high-speed, continuous-web rotary press lamination.

High-bond strength resists edge lifting.

Film liner offers superior graphic appearance for metalised or darker colours.

ScotchCap brand Overlaminating Films are Underwriters' Laboratories Recognised (File MH11410).

**Physical Properties**  
Not for specification purposes  
(Calipers are nominal values)

<b>Facestock</b>	25 microns (1.0 thou) Matt Clear Polyester
<b>Adhesive</b>	20 microns (0.8 thou) #400 Hi-Tack Acrylic
<b>Liner</b>	63 microns (2.5 thou) #43 Densified Kraft Paper
<b>Shelf Life</b>	24 months from date of manufacture when properly stored at 22°C & 50 % Relative Humidity

**Physical Properties**  
Not for specification purposes

<b>Adhesion</b> 180° Peel (ASTM D3330)				
Surface	Initial 10 min. dwell		Conditioned for 3 days at Room Temperature	
	N/10mm	Oz./In.	N/10mm	Oz./In.
Stainless Steel	2.6	24	4.4	40
Polyester	2.6	24	3.7	34

180° Liner Release	Rate of Removal	Gram / 25mm Width
	2.3 m / min	14
	7.6 m / min	16

Date : July 2000  
Polyester Overlaminating Film  
7742

---

## Environmental Performance

The properties defined are based on four-hour immersions at room temperature, unless otherwise noted. Samples were applied to stainless steel 24 hours prior to immersions and were evaluated one hour after removal.

### Chemical Resistance

Chemical	Appearance
Isopropyl Alcohol	No Change
Detergent	No Change
Engine Oil at 121°C (250°F)	No Change
Water for 48 hours	No Change

### Temperature Resistance

149°C (300°F) for 24 hours	Slightly yellowing
-40°C (40°F) for 24 hours	No Change noted

### Humidity Resistance

24 hours at 38°C (100°F) at 100% relative humidity	No Change
--	-----------

---

## Applications

Protective overlaminates for label and nameplate graphics can be used on appliances, industrial equipment, tools etc.

Graphics requiring a high-gloss or matt appearance.

---

## Processing

### Printing:

Facestock are not print treated. Liner backside has anti-block coating which makes it difficult to achieve good ink anchorage when printing on back of liner. Call Customer Service for recommendations.

### Die Cutting:

Rotary or flat-bed after lamination.

---

## Special Considerations

For maximum bond strength, surface should be thoroughly cleaned and dried. A typical cleaning solvent is heptane or isopropyl alcohol.

CAUTION: Follow manufacturer's instructions when using solvents.

For best bonding conditions, application surface should be at room temperature or slightly higher. Low temperature surfaces, below 10°C (50°F), cause the adhesive to become firm and will not allow the adhesive to flow and develop intimate contact with the substrate.

Higher initial bonds are achieved through increased rub down pressure. Use maximum laminating pressure for best results.

3M and Scotchcap are trademarks of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



## Tapes & Adhesives Group

© 3M United Kingdom PLC 2000

3M United Kingdom PLC  
3M House, PO Box 1,  
Market Place,  
Bracknell, Berkshire,  
RG12 1JU

Product Information :  
Tel 0870 60 800 50  
Fax 0870 60 700 99

3M Ireland  
3M House, Adelphi Centre,  
Upper Georges Street,  
Dun Laoghaire, Co. Dublin,  
Ireland

Customer Service :  
Tel (01) 280 3555  
Fax (01) 280 3509