



Product Data Sheet

Lexan® 8B35 Film

Description

Lexan 8B35 is a one side velvet, one side matt transparent polycarbonate film.

Lexan 8B35 offers high temperature resistance, excellent dimensional stability as well as good printability without pre-treatment making it very suitable for multi-layer printing.

Typical applications include :

- control panel overlays
- remote control overlays
- high performance labels
- floor graphics
- in-mould decoration
- automotive instrument clusters
- HV/AC overlays
- appliance overlays

Texture	Gauge (mm)	Colour
velvet/matt	0.075	112
	0.125	
	0.175	
	0.250	
	0.375	
	0.500	

Lexan



Product Data Sheet

Lexan[®] 8B35 Film

Property	Test	Unit	Value+
Physical			
Specific Gravity	ISO 1183	g/cm ³	1.20
Water absorption, saturation, 23°C	ISO 62	%	0.35
Pencil Hardness	ASTM D3363	-	B
Optical			
Refractive index, 25°C	DIN 53491	-	1.586
Light Transmission, average	ASTM D1003	%	88-91
Gardner gloss @ 60° velvet side*	ISO 2813	%	3.0-4.5
matt side		%	5.0-15.0
Mechanical			
Tensile stress at yield	ISO R527	MPa	63
at break		MPa	70
Strain at break	ISO R527	%	120
Tensile Modulus	ISO R527	MPa	2350
Tear Strength initiation	ASTM D1004	kN/m	245
propagation	ASTM D1922	kN/m	10-20
Burst Strength, Mullen 25 micron	ASTM D774	N/mm ²	0.28
Fold Endurance, double 250 micron	MIT	folds	200
Thermal			
Tensile Heat Distortion, 0.35 N/mm ²	ASTM D1637	°C	150
DTUL, 1.8 N/mm ²	ISO 75	°C	135
Vicat Softening Temperature, B	ISO 306	°C	150
Specific Heat	ASTM C361	kJ/kg.°C	1.25
Coefficient of Thermal Expansion	DIN 53752	1/°C	6.8x10 ⁻⁵
Thermal Conductivity	DIN 52612	W/m.°C	0.20
Strain Relief, 135°C	ASTM D1204	%	<0.2
Brittleness Temperature	ASTM D746	°C	-135
Electrical			
Dielectric Strength at 23°C in Oil, Short Time, 250 micron	IEC 243-1	kV/mm	67
Relative Permittivity 50 Hz	IEC 250	-	2.99
1 MHz		-	2.93
Dissipation Factor 50 Hz	IEC 250	-	0.0009
1 MHz		-	0.010
Volume Resistivity	IEC 93	Ohm.m	10 ¹⁴
Surface Resistivity	IEC 93	Ohm	10 ¹⁵
Arc Resistance, Tungsten	ASTM D495	s	120

+ Typical values only. Variations within normal tolerances are possible for the various textures.

* Gardner gloss measured after screenprinting matt side Flat Back.

Lexan[®] 8B35 Film

Typical Film Properties

Property	Unit	Value
Scratches	mm	<6 Hairline, Buff Type
Web Edge Curl*		
Machine direction	mm	<2.5
Transverse direction	mm	<12.3
Defect Size		
> 0.6 mm	Nr.	2/10m ²
> 0.4 mm	Nr.	2/0.1m ²
> 0.1 mm	Nr.	20/0.1m ²
Nominal Gauge		
Variation < 0.375 mm	%	10 %
>= 0.375	%	5 %

* Films from 375 to 750 micron gauge may contain curl due to roll set. This property can be minimized by double reverse winding the rolls approximately 48 hours prior to sheeting.



GE Plastics
Structured Products

General Electric Plastics bv
Plasticslaan 1, P.O. Box 117
4600 AC Bergen op Zoom
The Netherlands

Since General Electric Plastics B.V. tests are carried out under laboratory conditions and General Electric Plastics B.V. has no control over the use to which others may put this material, it does not guarantee that the same results as those described herein will be obtained under actual use conditions. Nor does General Electric Plastics B.V. guarantee the efficacy or safety of any possible or suggested design for articles of manufacture as illustrated herein by any photographs, technical drawings and the like. Each user of the material or design or both should make its own tests to determine the suitability of the material or any material for the design, as well as the suitability of the material or design or both for its actual use conditions. Statements concerning possible or suggested use of the materials or designs described herein are not to be construed as constituting a license under any General Electric Company or General Electric Plastics B.V. patent covering such use or as recommendations for use of such materials or designs in the